

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
3 November 2005 (03.11.2005)

PCT

(10) International Publication Number
WO 2005/103157 A1

(51) International Patent Classification⁷: **C08L 83/12**,
C08J 3/205

(21) International Application Number:
PCT/US2005/013289

(22) International Filing Date: 19 April 2005 (19.04.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/563,663 20 April 2004 (20.04.2004) US

(71) Applicant (for all designated States except US): **DOW CORNING CORPORATION** [US/US]; 2200 West Salzburg Road, Midland, MI 48686-0994 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **LIN, Shaow** [US/US]; 2008 Candlestick Lane, Midland, MI 48642 (US).

(74) Agent: **ZOMBECK, Alan**; Patent Department - Mail C01232, Dow Corning Corporation, 2200 West Salzburg Road, Midland, MI 48686-0994 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **SILICONE VESICLES**

(57) Abstract: A process for preparing a vesicle composition based upon mixing an organopolysiloxane having at least one hydrophilic substituent group, a water miscible volatile solvent, and water is disclosed. The vesicle compositions produced by the method are useful in various personal, household, and health care applications.

WO 2005/103157 A1

SILICONE VESICLES

Description

5

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to US Patent Application No. 60/563,663 as filed, April 20, 2004.

10 FIELD OF THE INVENTION

[0002] The present invention provides a process for preparing silicone vesicles by combining and mixing an organopolysiloxane having at least one hydrophilic substituent group, a water miscible volatile solvent, and water. The invention also relates to the vesicle compositions produced by the method and their use in various personal, household, and health care applications.

15

BACKGROUND OF THE INVENTION

[0003] Silicone surfactants have been designed for various applications by combining a hydrophobic organopolysiloxane with various hydrophilic moieties. For example, the silicone surfactants known as silicone polyethers are based on copolymer structures of polydimethylsiloxane having pendant polyoxyalkylene groups. Such materials find wide utility in many personal, household, and health care compositions as emulsifiers, wetting agents, and general-purpose aqueous surfactants.

20

[0004] The aggregation behavior of silicone polyethers has been discussed along with their ability to form vesicles. For example, US Patents 5,364,633 and 5,411,744 by Hill teaches the self-assembly of silicone vesicles in aqueous dispersions of certain silicone polyethers. PCT application US03/38455 by Lin teaches the entrapment of various oils in silicone vesicles and their use in various personal care formulations.

25

[0005] While these references represent advancements in the art, a need still exists to create silicone vesicles having improved stability. For example, the silicone vesicles formed from the self-assembly procedures can lack durability. This lack of durability can limit the processing conditions they can be subject to in the formation of various finished products.

30

Furthermore, such self-assembled silicone vesicles can lack the ability to provide sustained release of loaded actives over an extended period of time. Thus, a need exists for a process to prepare silicone vesicles having improved durability and the ability to release loaded actives over an extended period of time.

- 5 [0006] The present inventors have discovered a process to prepare silicone vesicles having improved durability and the ability to release loaded actives over an extended period of time.

SUMMARY OF THE INVENTION

- 10 [0007] The present invention provides a process for preparing a vesicle composition comprising;
- I) combining
 - A) an organopolysiloxane having at least one hydrophilic substituent group,
 - B) a water miscible volatile solvent,with water to form an aqueous dispersion,
 - 15 II) mixing the aqueous dispersion to form vesicles,
 - III) optionally, removing the water miscible volatile solvent from the vesicles.

- [0008] The present invention also relates to the vesicle compositions obtained from the inventive process, and the vesicle compositions further comprising a personal, household, health care ingredient.

20 [0009] The present invention further relates to personal, household, health care product compositions containing the vesicle compositions.

DETAILED DESCRIPTION OF THE INVENTION


- 25 [0010] The first step in the process of the present invention involves combining;
- A) an organopolysiloxane having at least one hydrophilic substituent group,
 - B) a water miscible volatile solvent,
- with water to form an aqueous dispersion.

- 30 [0011] Component A) is an organopolysiloxane having at least one hydrophilic substituent group. Organopolysiloxanes are well known in the art and are often designated as comprising any number of "M" siloxy units ($R_3SiO_{0.5}$), "D" siloxy units (R_2SiO), "T" siloxy units ($RSiO_{1.5}$), or "Q" siloxy units (SiO_2) where R is independently any hydrocarbon group. In the present


invention, the organopolysiloxane has at least hydrophilic substituent. That is, at least one of the R hydrocarbon groups present in the organopolysiloxane is a hydrophilic group. For purposes of this invention, "hydrophilic group" is the accepted meaning in the art, i.e., designating water loving chemical moieties. Thus, the hydrophilic group can be selected from various cationic, anionic, zwitterionic, polyoxyalkylene, oxoazoline chemical moieties that are commonly used in combination with various hydrophobic chemical moieties to create surfactant structures or molecules having surface-active behavior.

[0012] The amount of the hydrophilic substituent on the organopolysiloxane can vary, depending on the specific chemical component, providing there is at least one hydrophilic group present on the organopolysiloxane. However, the amount of the hydrophilic groups present in the organopolysiloxane can be described by its weight percent, or in particular, the weight percent of the organopolysiloxane and weight percent of the total hydrophilic groups present in the molecule. Typically, the weight percent of the siloxane units in the organopolysiloxane can vary from 20 to 85, alternatively from 30 to 85, or alternatively from 35 to 80 weight percent, while the remaining weight portion of the organopolysiloxane is the hydrophilic group.

[0013] In one embodiment of the present invention, the organopolysiloxane having at least one hydrophilic substituent group is selected from silicone polyethers. Silicone polyethers (SPEs) generally refer to silicones containing polyether or polyoxyalkylene groups, which encompasses many different structural forms. Two common forms are the rake-type or ABA type. In this embodiment, component (A) is a silicone polyether and can have a structure represented by:



A cyclic polyether of the type shown below can also be used.



In these structures, R1 represents an alkyl group containing 1-6 carbon atoms such as methyl, ethyl, propyl, butyl, pentyl, and hexyl; R2 represents the group -

- 5 (CH₂)_aO(C₂H₄O)_b(C₃H₆O)_cR₃; x has a value of 1-1,000, alternatively 1 - 500, or alternatively 10 - 250; y has a value of 1-500, alternatively 1 - 100, or alternatively 2 - 50; z has a value of 1-500, or alternatively 1 - 100; m has a value of 3-5; n is one; a has a value of 3-6; b has a value of 4-20; c has a value of 0-5; and R₃ is hydrogen, a methyl group, or an acyl group such as acetyl. Typically, R₁ is methyl; b is 6-12; c is zero; and R₃ is hydrogen.

10 **[0014]** The silicone surfactants can be prepared by any of the techniques known in the art, and many are commercially available. For example, rake type SPEs are derived most commonly from hydrosilylating SiH sites of MD_xD'_yM with allyloxy-functional polyethers in the presence of Pt catalyst.

15 **[0015]** The process of the present invention is particularly useful to prepare silicone vesicle compositions containing a silicone polyether having silicone/polyether molar ratios such that the silicone polyether aqueous solubility varies from those having only slightly water solubility or dispersibility to insoluble ones. This silicone/polyether ratio can be represented as value of x/y or x/z in the silicone polyether structures shown above and typically ranges from 5/1 to 50/1, alternatively from 10/1 to 50/1, or alternatively from 20/1 to 50/1. Such silicone polyethers are prepared from a SiH functional organopolysiloxane having a D/D' ratio ranging from 5/1 to 50/1, alternatively from 10/1 to 50/1 or alternatively from 20/1 to 50/1, where D' represents a SiH disiloxy unit (for example MeHSiO).

20 **[0016]** Component B) is a water-miscible volatile solvent. As used herein "water-miscible" means the solvent forms a dispersion with water at room temperature for at least several hours. "Volatile" means the solvent has a higher vapor pressure than water at various temperatures. As such, when the aqueous dispersion of the organopolysiloxane and solvent are subjected to conditions to remove the solvent, such as heating the dispersion under

reduced pressures, the solvent is primarily removed first, allowing all or most of the water to remain in the composition.

[0017] Suitable water-miscible volatile solvents for vesicle dispersion preparation include organic solvents such as alcohols, ethers, glycols, esters, acids, halogenated hydrocarbons, diols. The organic solvents should be miscible with water at the proportion and lower in order to effectively disperse silicones and maintain stable and uniform dispersion overtime. For the purpose of illustration, water-miscible alcohols include methanol, ethanol, propanol, isopropanol, butanol, and higher hydrocarbon alcohols; ethers include glycol ethers, methyl-ethyl ether, methyl isobutyl ether (MIBK), etc; glycols include propylene glycols, esters include esters of triglycerol, the esterification products of acid and alcohol; halogenated hydrocarbons include chloroform. Typically water-miscible organic solvents are solvents with relatively low boiling points ($<100^{\circ}\text{C}$) or high evaporation rate, so they may be removed under vacuum with ease. The most preferred water-miscible organic solvents for this invention are volatile alcohols including methanol, ethanol, isopropanol, and propanol. These alcohols can be removed from aqueous mixtures containing silicone vesicle dispersions via vacuum stripping at ambient temperature.

[0018] The order of mixing components A), B), and C) is not critical, but typically A) and B) are first mixed and then water added to the mixture. There are no special requirements or conditions needed for effecting the mixing of components A), B), and C). The mixing can be conducted in a batch, semi-continuous, or continuous process.

[0019] The amount of components A), B), and C) can vary in the process, but typically range as follows;

A) 2 to 50 wt%, alternatively 2 to 25 wt %, or alternatively 2 to 15 wt%,

B) 2 to 50 wt%, alternatively 2 to 25 wt %, or alternatively 2 to 15 wt%,

C) sufficient amount to provide the sum of the wt% of A), B), and C) to equal 100%

The amount of B) water-miscible volatile solvent used to disperse the organopolysiloxane depends on the type of organopolysiloxane and how much hydrophilic groups are present. Typically, the aqueous mixture to effectively disperse silicones comprises of 5 to 80 parts of solvent and 20 to 95 parts of water; alternatively 5 to 50 parts of water, or alternatively 10 to 40 parts water.

[0020] Step II in the process of the present invention is mixing the aqueous dispersion formed in Step I to form vesicles. There are no special requirements or conditions needed to

effect the mixing and formation of vesicles. Mixing techniques can be simple stirring, homogenizing, sonalating, and other mixing techniques known in the art to effect the formation of vesicles in aqueous dispersions. The mixing can be conducted in a batch, semi-continuous, or continuous process.

5 [0021] The formation of vesicles can be confirmed by techniques common in the state of the art. Typically, vesicles have a lamellar phase structure which exhibit birefringence when examined with a cross polarizing microscope. Alternatively, the formation of vesicles can be demonstrated by Cyro-Transmission Electron Microscopy (Cryo-TEM) techniques. Particle size measurements can also be used to indicate that the organopolysiloxanes are sufficiently
10 dispersed in aqueous medium typical of vesicle sizes. For example, average particle sizes of less than 0.500 μm (micrometers), are typical for dispersed vesicles. Vesicles having an average particle size of less than 0.200 μm , or 0.100 μm are possible with the teachings of the present invention.

[0022] Step III in the process of the present invention is optional, and involves removing the
15 water miscible volatile solvent, component B). Typically, the water miscible volatile solvent is removed by known techniques in the art, such as subjecting the vesicle composition to reduced pressures, while optionally heating the composition. Devices illustrative of such techniques include rotary evaporators and thin film strippers.

[0023] The present invention also relates to the vesicle compositions produced by the
20 methods, as described supra. The formation of vesicles can be confirmed by techniques common in the state of the art. Typically, vesicles having a lamellar phase structure which exhibit birefringence when examined with a cross polarizing microscope. Alternatively, the formation of vesicles can be demonstrated by Cyro-Transmission Electron Microscopy (Cryo-TEM) techniques. Particle size measurements can also be used to indicate that the
25 organopolysiloxanes are sufficiently dispersed in aqueous medium typical of vesicle sizes For example, average particle sizes of less than 0.500 μm (micrometers), are typical for dispersed vesicles. Vesicles having a average particle size of less than 0.200 μm , or 0.100 μm are possible with the method of the present invention.

[0024] The present invention further relates to vesicle compositions further comprising a
30 personal, household, or health care ingredient. Thus, the vesicle compositions can be used to entrap, and subsequently deliver after application, a personal, household care, or health care ingredient. A listing of possible personal, household, or health care ingredients is taught in

WO 03/101412, which is incorporated herein by reference. The personal or health care ingredient can also be selected from a personal or health care "active", that is, any compound known to have either cosmetic and/or pharmaceutical activity. A representative listing of such personal or health care actives are disclosed in US Patent 6,168,782, which is hereby
5 incorporated by reference.

[0025] Compositions prepared according to the invention can be used in various over-the-counter (OTC) personal care compositions, health care compositions, and household care compositions, but especially in the personal care arena. Thus, they can be used in antiperspirants, deodorants, skin creams, skin care lotions, moisturizers, facial treatments
10 such as acne or wrinkle removers, personal and facial cleansers, bath oils, perfumes, colognes, sachets, sunscreens, pre-shave and after-shave lotions, liquid soaps, shaving soaps, shaving lathers, hair shampoos, hair conditioners, hair sprays, mousses, permanents, depilatories, hair cuticle coats, make-ups, color cosmetics, foundations, blushes, lipsticks, lip balms, eyeliners, mascaras, oil removers, color cosmetic removers, nail polishes, and
15 powders.

EXAMPLES

[0026] The following examples are presented to further illustrate the compositions and methods of this invention, but are not to be construed as limiting the invention. All parts and
20 percentages in the examples are on a weight basis and all measurements were obtained at about 23°C, unless indicated to the contrary.

[0027] The vesicle compositions were analyzed via Cryo-TEM techniques according to the following procedure. Around 2.3 µl of aqueous sample solution was loaded using a micropipette on a lacey carbon film coated Cu TEM grid that was cleaned and rinsed with
25 acetone and chloroform. The samples were diluted to about 5% solution with de-ionized water. The excess fluid on the grid surface was removed by blotting the surface with a filter paper for 1.5 second to make an aqueous thin film for TEM. The grid was then plunged into a liquid ethane contained in a small vessel located in a larger liquid nitrogen vessel under -175 °C atmosphere in the cryo-plunge system to vitrify the water film on the grid and to avoid
30 water crystallization. The quenched sample grid was transferred in to the cryo-grid box in the cryo-plunge system. The grid box containing the sample was transferred into a Gatan cryo-transfer system filled with liquid nitrogen and loaded in a cryo-TEM stage, which has been

positioned in the cryo-transfer system and cooled down to below -160°C . The sample was loaded in TEM (JEOL 2000FX) and the images were observed at below -160°C . A much colder finger, cooled to -180°C in TEM using liquid nitrogen, was present to reduce any possible contamination on the cold specimen surface under high vacuum during TEM analysis. The digital images, as shown herein, were taken using a Gatan CCD camera attached at the bottom of the TEM column and Digital Micrograph software.

Example 1 (Reference example)

Silicone polyethers used for preparation of vesicle dispersions.

[0028] A series of silicone polyethers were prepared, as illustrated in Table 1 below. This series were "rake type" silicone polyethers since they were derived from various dimethyl-methylhydrogen-polysiloxanes of the general formula, $\text{MD}_x\text{D}'_y\text{M}$ and allyloxy polyethers. The $\text{MD}_x\text{D}'_y\text{M}$ siloxanes were prepared according to known techniques. The silicone polyethers were prepared using well known platinum catalyzed hydrosilylation techniques, such as those disclosed in US Patent 2,823,218.

[0029] The D/D' ratio corresponds to x/y ratio in the formula $\text{MD}_x\text{D}'_y\text{M}$ and total DP is the sum of x and y . EO7 is allyloxyl poly(ethylene oxide) having about seven EO repeat units, and EO12 is allyloxyl poly(ethylene oxide) having about 12 EO repeat units; both were obtained from Dow Chemical Company (Midland, MI).

Table 1

Siloxane structure	$\text{MD}_{27}\text{D}'_3\text{M}$	$\text{MD}_{22}\text{D}'_2\text{M}$	$\text{MD}_{28.8}\text{D}'_{1.22}\text{M}$	$\text{MD}_{46.88}\text{D}'_{3.12}\text{M}$	$\text{MD}_{70}\text{D}'_3\text{M}$
D / D' ratio	9.0	10	15	15	23.3
Total dp, D+D'	30	24	30	50	73
EO7 polyether		SPE 1	SPE 2	SPE 3	
EO12 polyether	SPE 4	SPE 5	SPE 6	SPE 7	SPE 8

[0030] For $MD_xD'_yM$ rake-type SPEs, D/D' ratio represents the relative ratio of the number of siloxane repeat units to the number of polyether substituted units on the siloxane polyethers, and a direct measure of hydrophobic to hydrophilic ratio of the SPEs. The lower the D/D' ratio, the more hydrophilic the SPEs, and more readily dispersible the SPE is in water.

Example 2

Effect of D/D' ratio of SPEs and alcohol on vesicle dispersion preparation

[0031] SPEs were generally found to spontaneously disperse in water, forming vesicles, when the D/D' was 12 or lower, as summarized in Table 2 below. When the D/D' ratio of the SPE was 15 or higher, the SPEs were less dispersible in water, and the rate of SPE dispersion in water could be very slow to incomplete. This example demonstrates the time needed to disperse SPE 6 (from Example 1) in water and how much faster it disperses when a small amount of isopropanol was present.

[0032] When D/D' was greater than 15, the SPEs did not spontaneously disperse in water. For example, the SPEs derived from $MD_{70}D'_3M$ (such as SPE 8) were not dispersible at all in water, even over more than a period of 2 months.

[0033] Examples 2A and 2 B show how SPE 6, a silicone polyether of $MD_{28.8}D'_{1.22}M$ siloxane structure dispersed in water alone and in the presence of 5 % isopropanol, respectively. It took about 3 weeks of continuous mixing to form a homogeneous dispersion in water as opposed to less than 1 day when 5 % by weight of isopropanol present in water.

[0034] Homogeneous dispersions of SPE 3 and SPE 7, silicone polyethers of $MD_{46.88}D'_{3.12}M$ siloxane backbone with D/D' of 15, were also made into homogeneous dispersions within 2 days with aid of 5 % isopropanol, as shown in Examples 2C and 2D.

Table 2

Example	2A	2B	2C	2D
Process History	3 weeks of continuous mix	As mixed, uniform dispersion in 1 day	As mixed, homogeneous in 2 days	As mixed, uniform dispersion in 2 days
Formulation				
SPE 3 (D/D' = 15), g			10	
SPE 6 (D/D' = 15), g	10.02	10.09		
SPE 7, (D/D' = 15) g				10.03
Isopropanol, g		5.02	5.000	5.02
D.I. Water, g	90.030	85.3	85.000	85.3
Final Dispersion Composition				
Wt. % SPE	10.00	10.00	10.00	10.00
Wt. % Isopropanol	0.00	5.00	5.00	5.00
Wt. % Water	90.00	85.00	85.00	85.00
pH of the dispersion	5.99	6.52	6.2	6.22
Avg. dispersion size, μm				
D(v, 0.5), μm				
D(v, 0.9), μm				

- 5 [0035] Cryo-TEM images of the vesicles formed in Examples 2A, 2B, and 2D are shown in figures 1 – 3 respectively. These images show the presence of single lamellar vesicles in Example 2A, and presence of multi-lamellar vesicles in Examples 2B and 2D.

Example 3*Comparative example*

- 5 [0036] A dispersion of SPE 8 in water was attempted by incorporating 10.0 g of SPE 8 into 90.0 g of de-ionized water in a glass jar. The jar was subjected to mixing on a rotowheel mixer. Even after 4 weeks of mixing the SPE remained as separated in water, no dispersion was formed.

10 **Example 4**

Preparation of 20% and 30% SPE 8 Vesicle Dispersions

Example A4: Vesicle dispersion of 14.4% SPE 8 dispersion in 28.7% isopropanol and 56.9 % water.

- 15 [0037] A dispersion was prepared by first adding SPE 8 into isopropanol with continuous mixing. Then, water was gradually added with continuous stirring. The resulting final mixture was clear, and a homogenous dispersion. SPE vesicles of 31 nm average sizes were observed and the dispersion has a clear water-like appearance due to the size of the vesicles.

20 *Example 4B: Vesicle dispersion of 20.0% SPE 8 in 80.0 % water.*

- [0038] A homogeneous dispersion of SPE 8 in isopropanol and water was prepared, following a similar procedure for Example 4A. This dispersion was further stripped under vacuum at ambient temperature to remove volatile isopropanol using a Rotovapor. The
25 theoretical amount of 74.93 g of IPA was completely removed and yielded a theoretically alcohol-free aqueous dispersion of SPE 8 vesicles. The resultant product was a milky-white, homogeneous dispersion with an average particle size of 212 nm, as measured by Nanotracc particle analyzer.

30 *Example 4C: vesicle dispersion of 21.2% SPE 8 in 28.8% isopropanol and 50% water.*

- [0039] A homogeneous vesicular dispersion of 21 nm average particle size in isopropanol and water was prepared, following a procedure similar to that of Example 4A.

35

Example 4D: vesicle dispersion of 29.5 % SPE 8 in 1.0% isopropanol and 69.5% water

- [0040] A homogeneous vesicular dispersion of 436 nm average particle size in water was prepared, following a procedure similar to that of Example 4B. The final mixture was a milky-white, homogenous dispersion.

Example #	4A	4B	4C	4D
Process History	As mixed	Mixed, then stripped	As mixed	Mixed, then stripped
SH 3775M SPE, g	43.11	37.59	64.12	55.89
IPA, g	86.23	74.93	87.00	75.93
D.I. Water, g	170.724	148.55	151.268	131.82
Batch size, as mixed	300	261.07	302.4	263.64
IPA Removed, g		-75.70		-74.10
Final batch, after strip		185.37		189.53
Wt. % Polymer	14.4	20.0	21.2	29.5
Wt. % IPA	28.7	0.0	28.8	1.0
Wt. % Water	56.9	80.0	50.0	69.5
Appearance of dispersion	Clear water-like liquid	Milky white material	Clear water-like liquid	Milky white material
Avg. particle size, μm	0.031	0.212	0.021	0.436
D(v, 0.5), μm	0.029	0.178	0.019	0.353
D(v, 0.9), μm	0.044	0.428	0.036	0.914

Example 5***Effect of isopropanol concentration on vesicle dispersion size***

5 [0041] The ease of dispersing silicone polyethers and, in some cases, the size and structure of the vesicles in the final water dispersions depends on the amount of isopropanol. This example illustrates this effect with two rake-type SPEs, SPE 7 and 8 as identified in Example 1.

Examples 5A, 5B, and 5C

10

[0042] Dispersions of SPE 8 in water containing 5% to 20 wt.% isopropanol were prepared according to the procedure described previously, according to the formulations summarized in Table 5. Example 5C was prepared by subjecting the Example 5B dispersion to further vacuum stripping to remove most of the IPA.

15

Examples 5D and 5E

[0043] A homogeneous vesicle dispersion of SPE 7 was made in 20 % IPA and 70 % water having an average dispersion size of only 77 nm, according to the previously described procedure, as summarized as Example 5D. The isopropanol was removed by vacuum stripping, resulting in a dispersion (Example 5E) having an average dispersion size of only 49 nm in water, as summarized in Table 5.

20

Table 5

Example #	5A	5B	5C	5D	5E
Process History	As mixed	As mixed	Mixed, then stripped	As mixed	Mixed, then stripped
SH 3775M SPE, g	10.025	30.012	20		
18841-91 SPE, g				30.006	20.0
IPA, g	10.005	60.082	10	60.172	40.0
D.I. Water, g	80.044	210.063	140	210.757	140.0
Final Dispersion Composition					(-40 g alcohol)
Wt. % Polymer	10.02	10.00	11.76	9.97	12.50
Wt. % IPA	10.00	20.02	5.88	20.00	0.00
Wt. % Water	79.98	69.98	82.35	70.03	87.50
pH of the dispersion	5.87	7.14	6.81	6.35	6.38
Avg. dispersion size, um	1.427	0.106	0.099	0.077	0.049
D(v, 0.5), um	0.955	0.092	0.091	0.071	0.072
D(v, 0.9), um	3.789	0.178	0.156	0.112	0.104

- 5 [0044] Cryo-TEM images confirmed the silicone polyether dispersions were nano-scale vesicles and aggregates of vesicles. The actual sizes observed were consistent with the particle size measured by Nanotrak particle analyzer. The cryo-TEM images of SPE 8 dispersion (Example 5C) and that of SPE 7 dispersion (Example 5E) are shown in figures 4 and 5 respectively.

10

Example 6

SPE vesicle dispersions containing Vitamin A palmitate

- 15 [0045] The method of this invention can also be used to entrap and retain oil-soluble substances into vesicles in aqueous dispersions. This is very desirable and beneficial utility of vesicles and vesicular aggregates prepared from silicone polyethers. As many personal care actives & ingredients are not water-soluble or not water-compatible. This makes it not practical to incorporate such ingredients as vitamins, fragrances, sunscreens, and oils directly into water-based or water-continuous end-product formulations, such as creams, lotions, gels, etc.
- 20

[0046] This series of examples shows that vitamin A palmitate (a preferred form of vitamin A for skin care products) can be successfully incorporated into SPE based vesicles in water dispersions, using the method of this invention. Results and formulations are summarized in Table 6.

5

Examples 6A and 6B

Vitamin A palmitate entrapped SPE vesicles in partially and fully stripped aqueous dispersions.

[0047] Vitamin A palmitate (VAP) was first dispersed in isopropanol at 50/50 ratio by weight to keep VAP in a liquid form for ease of mixing. The VAP/IPA was then mixed in with SPE 8, followed by incorporation of isopropanol to form a homogeneous mixture. While under continuous mixing, water was gradually and continuously incorporated into the mixture containing the SPE, VAP and IPA. Then, the mixture was homogenized, using an APV benchtop homogenizer, to further narrow and reduce the dispersion size. The homogenized dispersion was subsequently stripped to remove isopropanol under vacuum at ambient temperature, using a Rotovapor.

[0048] The 6A example was a partially stripped dispersion having about 10% IPA remaining and an average dispersion size of 0.229 μm . The 6B example was a fully stripped dispersion containing 20.8% SPE, 4.5% VAP, 2.2% IPA and 72.5% water. Example 6B was a homogeneous, beige milky dispersion having an average vesicle size of 0.974 μm .

Example 6C

Vitamin A palmitate loaded dispersion made without homogenization using ethanol.

[0049] This dispersion was prepared by first dispersing vitamin A palmitate into SPE 8 in the presence of a small quantity of ethanol. The prescribed amount of ethanol was mixed in with SPE / VAP to form a homogeneous mixture. While under continuous mixing, water was gradually and continuously incorporated into the mixture. A homogeneous mixture was obtained. The mixture was then subjected to vacuum stripping to remove the volatile alcohol. The final dispersion had a composition of 4.5% VAP, 20.7% SPE, 2.9% EtOH and 72.0 % water. The dispersion had an average dispersion size of 0.763 μm .

*Examples 6D and 6E**Vitamin A palmitate loaded dispersions made with EtOH.*


[0050] Ethanol was used as dispersing aid to prepare these VAP loaded SPE vesicles in water dispersions. The procedures followed the ones that used to make Example 6A and 6B, except EtOH used in place of IPA. The final dispersion compositions are shown in Table 6. The two dispersions had an average dispersion size of 0.284 μm and 0.331 μm , respectively.

Table 6

Example #	6A	6B	6C	6D	6E
Alcohol type used	IPA	IPA	EtOH	EtOH	EtOH
Process History	Mixed, Homog., Partially Stripped	Mixed, Homog., Fully Stripped	Mixed, Stripped	Mixed, Homog., Partially Stripped	Mixed, Homog., Fully Stripped
VAP (vitamin A palmitate), g	3.96	3.91	9.89	3.94	3.69
Alcohol, g	32.71	32.32	81.61	32.54	30.50
SPE 8, g	18.35	18.13	45.73	18.23	17.09
Water, g	63.96	63.19	159.01	63.40	59.42
Batch size, as mixed, g	118.97	117.55	296.23	118.11	110.70
Alcohol Removed, g	23.48	30.37	75.30	22.21	28.47
Batch size, after strip, g	95.49	87.18	220.93	95.90	82.23
Final Dispersion composition					
Wt. % VAP	4.1	4.5	4.5	4.1	4.5
Wt. % Alcohol	9.7	2.2	2.9	10.8	2.5
Wt. % SPE Polymer	19.2	20.8	20.7	19.0	20.8
Wt. % Water	67.0	72.5	72.0	66.1	72.3
Appearance of Dispersion	Beige milky dispersion	Beige milky dispersion	Beige milky dispersion; small oil droplets atop	Beige milky dispersion	Beige milky dispersion
Average particle size, μm	0.2291	0.974	0.763	0.2842	0.331
D(v, 0.5), μm	0.1602	0.995	0.374	0.1624	0.2103
D(v, 0.9), μm	0.513	1.783	1.987	0.727	0.785

Claims

1. A process for preparing a vesicle composition comprising;
 - I) combining
 - A) an organopolysiloxane having at least one hydrophilic substituent group,
 - B) a water miscible volatile solvent,
 with water to form an aqueous dispersion,
 - II) mixing the aqueous dispersion to form vesicles,
 - III) optionally, removing the water miscible volatile solvent from the vesicles.
2. The process of claim 1 wherein the aqueous dispersion contains;
 - A) 5 to 50 wt % of the organopolysiloxane,
 - B) 5 to 50 wt% of the water miscible solvent,
 - C) sufficient amount of water
 to provide the sum of the wt% of A), B), and C) to equal 100 wt %.
3. The process of claim 1 wherein the organopolysiloxane is a silicone polyether.
4. The process of claim 1 wherein the organopolysiloxane is a silicone polyether having a structure represented by:



where R1 represents an alkyl group containing 1-6 carbon atoms;


R2 represents the group $-(CH_2)_aO(C_2H_4O)_b(C_3H_6O)_cR_3$;

x is 1-1,000; y is 1-500; z is 1-500; a is 3-6; b is 4-20; c is 0-5;

and R3 is hydrogen, a methyl group, or an acyl group.

5

5. The process of claim 1 wherein the silicone polyether has the structure,



x is from 1 to 1000, y is from 1 to 500, R1 is methyl,

10

R2 represents the group $-(CH_2)_aO(C_2H_4O)_b(C_3H_6O)_cR_3$

where a is 3-6; b is 4-20; c is 0-5, and R3 is hydrogen, a methyl group, or an acyl group.

6. The process of claim 5 wherein the ratio of x/y is from 5/1 to 50/1.

15

7. The process of claim 1 wherein the water miscible volatile solvent is an alcohol.

8. The process of claim 1 wherein the water miscible volatile solvent is isopropyl alcohol.

20

9. The product resulting from the process of any one of claims 1 – 8.

10. A personal, household, or health care product comprising the product of claim 9.


Figure 1


Figure 2


Figure 3

Figure 4





Figure 5



A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08L83/12 C08J3/205

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08L C08J A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 483 465 A (SALAMA, ZOSER BOULIS, DR; RICHTER, HEINRICH, DOZ. DR. SC; MEYER, HELMU) 6 May 1992 (1992-05-06) claims; examples 4-7	1,2,9,10
X	EP 0 724 876 A (DOW CORNING CORPORATION) 7 August 1996 (1996-08-07) claims; examples	9,10
X	US 5 958 433 A (SIMONNET ET AL) 28 September 1999 (1999-09-28) the whole document	9,10
X	US 2003/220425 A1 (FERRITTO MICHAEL SALVATORE ET AL) 27 November 2003 (2003-11-27) claims; examples	9,10

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

16 August 2005

Date of mailing of the international search report

29/08/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kolitz, R

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0483465	A	06-05-1992	DD 297249 A5	02-01-1992
			DE 59106138 D1	07-09-1995
			EP 0483465 A1	06-05-1992
EP 0724876	A	07-08-1996	US 5958448 A	28-09-1999
			CA 2166455 A1	14-07-1996
			DE 69514776 D1	02-03-2000
			DE 69514776 T2	31-08-2000
			EP 0724876 A2	07-08-1996
			ES 2144584 T3	16-06-2000
			JP 8239475 A	17-09-1996
US 5958433	A	28-09-1999	FR 2742674 A1	27-06-1997
			DE 69623423 D1	10-10-2002
			DE 69623423 T2	09-01-2003
			EP 0780113 A1	25-06-1997
			ES 2182958 T3	16-03-2003
			JP 3137592 B2	26-02-2001
			JP 9175930 A	08-07-1997
US 2003220425	A1	27-11-2003	US 2003032717 A1	13-02-2003
			DE 60201982 D1	23-12-2004
			EP 1377621 A2	07-01-2004
			JP 2004527618 T	09-09-2004
			WO 02083759 A2	24-10-2002
			AU 4164302 A	01-07-2002
			EP 1343834 A2	17-09-2003
			EP 1348004 A2	01-10-2003
			JP 2004526001 T	26-08-2004
			JP 2004521174 T	15-07-2004
			WO 0250166 A2	27-06-2002
			WO 02059211 A2	01-08-2002
			US 2003050393 A1	13-03-2003
			US 2002086935 A1	04-07-2002

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)